



400N



GEI 400N is a needlepunched nonwoven geotextile manufactured using polypropylene fibers that are formed into a dimensionally stable network, which allows the fibers to maintain their relative position.

GEI 400N resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	100 x 100 lbs	445 x 445 N
Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	310 lbs	1380 N
Trapezoidal Tear	ASTM D-4533	45 x 45 lbs	200 x 200 N
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	70 US Std. Sieve	0.212 mm
Permittivity	ASTM D-4491	2.0 sec ⁻¹	2.0 sec ⁻¹
Water Flow Rate	ASTM D-4491	140 gpm/ft ²	5704 lpm/m ²

*Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241

PROPERTY	Typical English	Typical Metric
Roll Dimensions	12.5 x 360 ft 15 x 360 ft	3.81 x 109.8 m 4.6 x 109.8 m
Roll Area	500 yd ² 600 yd ²	418 m ² 502 m ²

Disclaimer: GEI Works assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. GEI Works disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation and implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.